

東城石油化工有限公司

East Town Petroleum & Chemicals Ltd.

Unit D-E, 16/F Golden Sun Centre, 59-67 Bonham Strand West, Hong Kong

Tel: + (852) 2541 2417, Fax: + (852) 2541 8386

Email: easttown@live.hk <http://www.easttown.com.hk>

PRODUCT SPECIFICATION

PARAFFIN WAX

Product Item		Melting Point (Deg. °C)	Melting Point (Deg. °F)	Oil Content Wt / % Max.	Color, Saybolt Min.	Light Stability Max.	Needle Penetration (25° C, 100g), 1/10mm max.
Fully Refined Paraffin Wax	FR54/56	54/56	129-133	≤0.5	≥+28	≤4	≤19
	FR56/58	56/58	133-136	≤0.5	≥+28	≤4	≤19
	FR58/60	58/60	136-140	≤0.5	≥+25	≤5	≤18
	FR60/62	60/62	140-144	≤0.5	≥+25	≤5	≤18
	FR62/64	62/64	144-148	≤0.5	≥+25	≤5	≤18
Semi Refined Paraffin Wax	SR54/56	54/56	129-133	≤1.5	≥+17	≤6	≤20
	SR56/58	56/58	133-136	≤1.5	≥+17	≤6	≤20
	SR58/60	58/60	136-140	≤1.5	≥+17	≤6	≤20
	SR60/62	60/62	140-144	≤1.5	≥+17	≤6	≤20
Test methods	ASTM D87		ASTM D721	ASTM D156	SH/T0404	ASTM D1321	

Packing : in 25kgs / 50kgs, pp or pe woven bag

Quantity : 20 MT per 20' FCL

Payment : T/T or L/C at sight

Delivery : around 2 weeks up on receipt of confirmed payment

Note : The information contained herein only for reference, it is to our best knowledge, true and accurate, but all recommendations or suggestion are made without guarantee, due to the condition of use are beyond our control. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In submitting this information, no liability is assumed or license or other rights express or implied given with respect to any existing or pending patent, patent applications or trademarks. The observance of all legal regulations and patent is the responsibility of user.